BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	ALDER	steamed
		31 <u>C</u> Q111 <u>C</u> Q

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water,

> the Alder without heartwood receives a light brown, reddish colour with decent brown colour inclusions. The sorting Klassiker is essentially knot-free*, with a simple

structure.

Brinell hardness 1,7 kp Gross density 0,49 g | cm³

2-Strip Plank Flooring ALDER steamed "Klassiker"



Surfaces

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **✓** Brushed
- **▼** Bevel
- ✓ Special colour



Sorting guidelines		
Healthy knots	to approx. 5 mm allowed	
Black knots	to approx. 5 mm allowed	
Healthy red heart	not allowed	
Healthy black heart	not allowed	
Cracks	not allowed	
Curled Spots differences in structure	allowed	
Natural colour differences	slightly allowed	
Natural fiber orientation	partly allowed	
Wormholes and insect-ate-spots	not allowed	
Sapwood	not allowed	
Red or brown spots	not allowed	
Stains from storage and light blueness	not allowed	
Knocked spots	not allowed	
Mirror	not allowed	

Technical data		
Thickness Width	15 mm 140 mm	Useful layer approx. 5 mm
Length	Length Fixlength (8 layers pkg)	8 layers 2400 mm
Connection Tongue and groove		ove

m² pkg. 2,69	m² pal. 112,98			
kg pkg. 26,2	kg pal. 1104			
Floating laving				

- ✓ Floating laying
- ✓ Glued laying
- ✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure