BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	DEECH	
	BEECH	steamed

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander

water, the Beech receives a light, slightly reddish to deep reddish brown colour.

The sorting Wohngefühl is knotty, with a medium structure.

Brinell hardness 4,0 kp Gross density 0,72 g | cm³

1-Strip Country House Flooring BEECH steamed Wohngefühl "Bregenz"



Surfaces

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour

also available as

✓ Systemboard (Fixlength 1100 mm)



Sorting guidelines			
Healthy knots	allowed (partly filled)		
Black knots	to approx. 35 mm allowed (partly filled)		
Healthy red heart	not allowed		
Healthy black heart	not allowed		
Cracks	slightly allowed (partly filled)		
Curled Spots differences in structure	slightly allowed		
Natural colour differences	allowed		
Natural fiber orientation	to one-third allowed		
Wormholes and insect-ate-spots	not allowed		
Sapwood	not allowed		
Red or brown spots	slightly allowed		
Stains from storage and light blueness	not allowed		
Knocked spots	not allowed		
Mirror	allowed		

		Sym	nbol picture - may vary in colour and structure	
Technical data				
Thickness Width	Width 150 mm		Useful layer approx. 5 mm	
Length			6 layers 1900 mm 2 layers 950* mm	
Connection Tongue and groove				
One layer 950* mm consists of 2 boards				
m² pkg. 2,28		ľ	m² pal. 111,72	
kg pkg. 23		ŀ	kg pal. 1127	
✓ Floating laying				

✓ Glued laying

✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure