

Woodtype **BEECH steamed**

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Beech receives a light, slightly reddish to deep reddish brown colour. The sorting Auslese is essentially knot-free*, with a simple structure.

Brinell hardness 4,0 kp
 Gross density 0,72 g | cm³

1-Strip Country House Flooring BEECH steamed Auslese „Klagenfurt“



Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Bevel



Symbol picture - may vary in colour and structure

Sorting guidelines	
Healthy knots	to approx. 5 mm allowed (partly filled)
Black knots	to approx. 10 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	not allowed
Curled Spots differences in structure	slightly allowed
Natural colour differences	slightly allowed
Natural fiber orientation	slightly allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	slightly allowed

Technical data		
Thickness	15 mm	Useful layer approx. 5 mm
Width	150 mm	
Length	Lengthsystem	6 layers 1900 mm
	(8 layers pkg)	2 layers 950* mm
Connection	Tongue and groove	
One layer 950* mm consists of 2 boards		
m² pkg. 2,28		m² pal. 111,72
kg pkg. 23		kg pal. 1127
<input checked="" type="checkbox"/> Floating laying		
<input checked="" type="checkbox"/> Glued laying		
<input checked="" type="checkbox"/> Suitable for underfloor heating		
when gluing the entire area with solvent-free adhesives		

