BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	DEECT	
	BEECH	steamed

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water,

the Beech without heartwood receives a light, slightly reddish to deep reddish brown colour. The sorting Klassiker is essentially knot-free\*, with a simple structure.

Brinell hardness 4,0 kp

Gross density 0,72 g | cm³

## 2-Strip Plank Flooring BEECH steamed "Klassiker"



## Surfaces


- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel



Sorting guidelines	
Healthy knots	to approx. 5 mm allowed (partly filled)
Black knots	to approx. 5 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	not allowed
Curled Spots   differences in structure	not allowed
Natural colour differences	slightly allowed
Natural fiber orientation	partly allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	slightly allowed

		Symbol picture - may vary in colour and structure	
Technical data			
Thickness Width Length	15 mm 140 mm Fixlength (8 layers   pkg)	Useful layer approx. 5 mm	
		8 layers 2400 mm	
Connection Tongue and groove			
m <sup>2</sup>  pkg. 2,69		m²   pal. 112,98	
kg pkg. 26,2		kg pal. 1104	
✓ Floating laying			
✓ Glued laying			
☑ Suitable for underfloor heating			

when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure