

Woodtype **ELM steamed**

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Elm receives a light brown to dark brown colour. The sorting Design is slightly to very knotty, with a lively structure.

Brinell hardness 4,3 kp
 Gross density 0,65 g | cm³

1-Strip Country House Flooring ELM steamed Design „Bern“



Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Bevel
- Special colour

also available as

- Systemboard
(Fixlength 1100 mm)



Symbol picture - may vary in colour and structure

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	allowed (partly filled)
Curlted Spots differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data		
Thickness	15 mm	Useful layer approx. 5 mm
Width	150 mm	
Length	Lengthsystem	6 layers 1900 mm
	(8 layers pkg)	2 layers 950* mm
Connection Tongue and groove		
One layer 950* mm consists of 2 boards		
m² pkg. 2,28		m² pal. 111,72
kg pkg. 23		kg pal. 1127
<input checked="" type="checkbox"/> Floating laying		
<input checked="" type="checkbox"/> Glued laying		
<input checked="" type="checkbox"/> Suitable for underfloor heating		
when gluing the entire area with solvent-free adhesives		



Symbol picture - may vary in colour and structure