

Woodtype **ELM steamed**

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Elm receives a light brown to dark brown colour. The sorting Trend-Epoca is knotty, with a lively structure.

Brinell hardness 4,3 kp
 Gross density 0,65 g | cm³

2-Strip Plank Flooring ELM steamed „Trend-Epoca”



Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	allowed (partly filled)
Curlted Spots differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data						
Thickness	15 mm	Useful layer approx. 5 mm				
Width	140 mm					
Length	Fixlength	8 layers 2400 mm				
	(8 layers pkg)					
Connection	Tongue and groove					
<table border="1" style="width: 100%;"> <tr> <td>m² pkg. 2,69</td> <td>m² pal. 112,98</td> </tr> <tr> <td>kg pkg. 26,2</td> <td>kg pal. 1104</td> </tr> </table>			m² pkg. 2,69	m² pal. 112,98	kg pkg. 26,2	kg pal. 1104
m² pkg. 2,69	m² pal. 112,98					
kg pkg. 26,2	kg pal. 1104					
<input checked="" type="checkbox"/> Floating laying						
<input checked="" type="checkbox"/> Glued laying						
<input checked="" type="checkbox"/> Suitable for underfloor heating						
when gluing the entire area with solvent-free adhesives						

