TYPES OF WOOD ALDER natural|steamed - ASH - BEECH natural|steamed - BIRCH BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	MAPLE european
Description	3 layers of the same hardwood. The Maple has a very gentle whitish to yellowish colour. The sorting Wohngefühl is knotty, with a medium structure.
Brinell hardness Gross density	3,2 kp 0,63 g cm³

1-Strip Country House Flooring MAPLE european Wohngefühl "Ischl"

Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- ✓ Untreated sanded
- Sevel
- Special colour

also available as

Systemboard (Fixlength 1100 mm)



Tochnical data

Symbol picture - may vary in colour and structure

Sorting guidelines			
Healthy knots	allowed (partly filled)		
Black knots	to approx. 35 mm allowed (partly filled)		
Healthy red heart	not allowed		
Healthy black heart	not allowed		
Cracks	slightly allowed (partly filled)		
Curled Spots differences in structure	slightly allowed		
Natural colour differences	allowed		
Natural fiber orientation	to one-third allowed		
Wormholes and insect-ate-spots	not allowed		
Sapwood	not allowed		
Red or brown spots	slightly allowed		
Stains from storage and light blueness	not allowed		
Knocked spots	not allowed		
Maple bar	partly alongside and crosswise allowed		

lechnical data				
Thickness Width	15 mm 150 mm	Useful layer approx. 5 mm		
Length	Lengthsyster (8 layers pkg			
Connection Tongue and groove				
One layer 950* mm consists of 2 boards				
m² pkg. 2,28		m² pal. 111,72		
kg pkg. 23		kg pal. 1127		
✓ Floating laying				
☑ Glued laying				
Suitable for underfloor heating when gluing the entire area with solvent-free adhesives				

www.bergland-parkett.at

