BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype Maple european

3 layers of the same hardwood. The Maple has a very gentle whitish to yellowish Description

colour. The sorting Auslese is essentially knot-free*, with a simple structure.

Brinell hardness 3,2 kp Gross density 0,63 g | cm³

1-Strip Country House Flooring MAPLE european Auslese "Salzburg"

Surfaces

- Oil | wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **▼** Bevel
- ✓ Special colour



✓ Glued laying

✓ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives

Sorting guidelines	
Healthy knots	to approx. 5 mm allowed
Black knots	to approx. 5 mm allowed
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	not allowed
Curled Spots differences in structure	slightly allowed
Natural colour differences	slightly allowed
Natural fiber orientation	partly allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Maple bar	not allowed

	Sy	ymbol picture - may vary in colour and structure
Technical data		
Thickness 15 mm Width 150 mm	. •	Useful layer approx. 5 mm
	Lengthsystem (8 layers pkg)	
Connection Tongue and groove		
One layer 950* mm consists of 2 boards		
m² pkg. 2	2,28	m² pal. 111,72
kg pkg. 2	23	kg pal. 1127
✓ Floating Id	aying	

