BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	OAK	european
----------	-----	----------

Description 3 layers of the same harwood. The European Oak has a middle brown to intensive

brown colour. The sorting Auslese is essentially knot-free*, with a simple structure.

Brinell hardness 4,2 kp Gross density 0,71 g | cm³

1-Strip Country House Flooring OAK european Auslese "Wien"



Surfaces

- Oil | wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **✓** Brushed
- **▼** Bevel
- ✓ Special colour




Sorting guidelines	
Healthy knots	to approx. 5 mm allowed
Black knots	to approx. 5 mm allowed
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	not allowed
Curled Spots differences in structure	slightly allowed
Natural colour differences	slightly allowed
Natural fiber orientation	slightly allowed
Wormholes and insect-ate-spots	not allowed are allowed in middle layer and back layer**
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

		Symbol picture - may vary in colour and structure		
Technical data				
Thickness Width Length	15 mm 150 mm Lengthsyste (8 layers pkg	,		
Connection Tongue and groove Due to the technical drying, there are no longer any pests, only the holes in the middle layer 950* mm consists of 2 boards layer and back layer**				
m² pkg.	2,28	m² pal. 111,72		
kg pkg.	23	kg pal. 1127		
✓ Floating laying				
✓ Glued laying				

✓ Suitable for underfloor heating

when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure