BLACK WALNUT steamed - CHERRY natural|steamed - ELM steamed

MAPLE - OAK - PEAR steamed - SMOKED OAK - SMOKED ZIRNOAK



Woodtype	OAK	european
		Colopcal

Description 3 layers of the same hardwood. The European Oak has a middle brown

to intensive brown colour. The sorting Trend-Epoca is knotty, with a lively

structure.

Brinell hardness 4,2 kp Gross density 0,71 g | cm³

2-Strip Plank Flooring OAK european "Trend-Epoca" white



Surfaces

- Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- **✓** Brushed
- **▼** Bevel



Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy black heart	not allowed
Cracks	allowed (partly filled)
Curled Spots differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	partly allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	alongside and crosswise allowed

	3y	mbol picture - may vary in colour and structure
Technical data		
Thickness Width	15 mm 140 mm	Useful layer approx. 5 mm
Length	Fixlength	8 layers 2400 mm
	(8 layers pkg)	
Connection	Tongue and gro	ove

m² pkg. 2,69	m² pal. 112,98
kg pkg. 26,2	kg pal. 1104
T Floating laving	

- ✓ Floating laying
- ✓ Glued laying
- ✓ Suitable for underfloor heating when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure